



HYDROPHILIC COMPRESSION SEALS NEOPRENE RUBBER COMPOUND CRS-656 CHEMICAL RESISTANCE SHEET

The following results have been obtained through Chemical resistance tests completed in accordance with ASTM Test Method D543

Legend:

- E = Excellent Service
- G = Good Service
- F = Fair
- N = Not recommended

Table:

Product	Concentration (%)	Chemical Resistance
Tap water (pH 6–9)	100	G
Nitric acid	5	N
Phosphoric acid	10	F
Sulfuric acid	10	F
Gasoline	100	N
Vegetable oil	100	F
Detergent	0.1	G
Soap	0.1	G